

Adhesive for convolute containers

Item/Performance		homaprom 1503 and its viscosity modifications	homaprom 1505
AREA OF APPLICATION	Cardboard tube production	■	■
	Convolute containers	■	■
PERFORMANCE	Adhesive power according to leatherette, N/m	NLT 250	NLT 350
	Adjustment time, applicator 150 µm, cardboard NP-200, s	55–65	45–55
	Base	Water polymer dispersion including functional additives.	
	Solid content, %	NLT 36	NLT 34
	pH	4,0–6,5	4,0–6,5
	Brookfield dynamic viscosity R2/20 @ 23°C, mPa*s	1000–3900	1000–2450
	Cold resistance	withstand five cycles of freeze (-20°C) / thawing (room temperature). Before processing thermostate the thawed product to the room temperature and stir.	